

PERCOM® FAH16FR

Polypropylene
A. Schulman Europe

Message:

PERCOM® FAH16FR is a Polypropylene material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Important attributes of PERCOM® FAH16FR are:
Flame Rated
RoHS Compliant
Flame Retardant
Typical applications include:
Electrical/Electronic Applications
Reflectors

General Information			
UL YellowCard	E132739-462578		
Additive	Flame Retardant		
Features	Flame Retardant		
Uses	Electrical Parts		
	Reflectors		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	0.920	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.0	g/10 min	ISO 1133
Molding Shrinkage	1.5 to 2.0	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	66		
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	30.0	MPa	ISO 527-2
Tensile Strain (Break)	80	%	ISO 527-2
Flexural Modulus	1600	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	3.5	kJ/m²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	150	°C	ISO 306/A50
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-2		UL 94
Glow Wire Ignition Temperature (2.00 mm)	960	°C	IEC 60695-2-13

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

