

LEXAN™ EXL1182T resin

Polycarbonate

SABIC Innovative Plastics

Message:

LEXAN EXL1182T polycarbonate (PC) siloxane copolymer resin is a UV stabilized, enhanced release transparent injection molding (IM) grade. This resin offers good low temperature (-20 C) ductility in combination with high flow characteristics and excellent processability with opportunities for shorter IM cycle times compared to standard PC resins. LEXAN EXL1182T resin is a UV stabilized, enhanced release product available in transparent and opaque colors and may be an excellent candidate for a broad range of applications.

General Information			
Additive	UV stabilizer		
Features	Copolymer		
	Workability, good		
	Fast molding cycle		
	High liquidity		
	Good demoulding performance		
	ductility		
RoHS Compliance	RoHS compliance		
Appearance	Opacity		
	Clear/transparent		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	20	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	19.0	cm³/10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.40 - 0.80	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.24	%	ISO 62
Equilibrium, 23°C, 50% RH	0.093	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2260	MPa	ASTM D638
--	2340	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	58.6	MPa	ASTM D638
Yield	57.8	MPa	ISO 527-2/50
Fracture ³	57.1	MPa	ASTM D638
Fracture	56.8	MPa	ISO 527-2/50

Tensile Elongation			
Yield ⁴	5.7	%	ASTM D638
Yield	5.4	%	ISO 527-2/50
Fracture ⁵	120	%	ASTM D638
Fracture	120	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁶	2250	MPa	ASTM D790
-- ⁷	2150	MPa	ISO 178
Flexural Stress			
--	89.5	MPa	ISO 178
Yield, 50.0mm span ⁸	94.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA
-30°C	18	kJ/m ²	ISO 179/1eA
23°C	61	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	620	J/m	ASTM D256
23°C	740	J/m	ASTM D256
-30°C ¹⁰	24	kJ/m ²	ISO 180/1A
23°C ¹¹	47	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	74.9	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	122	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹²	117	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	139	°C	ASTM D1525, ISO 306/B50 11 ¹³
--	140	°C	ISO 306/B120
Linear thermal expansion coefficient			
Flow: -40 to 95°C	7.5E-5	cm/cm/°C	ASTM E831
Flow: 23 to 80°C	7.5E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 95°C	7.6E-5	cm/cm/°C	ASTM E831
Lateral: 23 to 80°C	7.6E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 - 4.0	hr	
Drying Time, Maximum	48	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 60	%	
Rear Temperature	271 - 293	°C	
Middle Temperature	282 - 304	°C	

Front Temperature	293 - 316	°C
Nozzle Temperature	288 - 310	°C
Processing (Melt) Temp	293 - 316	°C
Mold Temperature	71.1 - 93.3	°C
Back Pressure	0.345 - 0.689	MPa
Screw Speed	40 - 70	rpm
Vent Depth	0.025 - 0.076	mm

NOTE

1.	50 mm/min
2.	Type 1, 50mm/min
3.	Type 1, 50mm/min
4.	Type 1, 50mm/min
5.	Type 1, 50mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4 sp=62mm
10.	80*10*4
11.	80*10*4
12.	80*10*4 mm
13.	速率 A (50°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT