Shanghai Potomer SG8

Rigid Polyvinyl Chloride

Shanghai Potomer International Trade Co., Ltd.

Message:

General Information

PVC suspension Resin is Calcium Carbide base, mainly used as sheet, pipe, window profiles and other molded parts. APPLICATIONS: fittings, electrical housings, bottles, rigid film, rigid foam

Features	High Rigidity		
Uses	Bottles		
	Electrical Housing		
	Film		
	Fittings		
	Foam		
Processing Method	Calendering		
	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	
Physical Apparent Density	Nominal Value > 0.48	Unit g/cm³	
<u> </u>			
Apparent Density	> 0.48		
Apparent Density K (wear) Factor	> 0.48		
Apparent Density K (wear) Factor Sieve Analysis	> 0.48 55.0 to 59.0	g/cm³	
Apparent Density K (wear) Factor Sieve Analysis 0.063mm sieve	> 0.48 55.0 to 59.0 > 90	g/cm³ %	
Apparent Density K (wear) Factor Sieve Analysis 0.063mm sieve 0.25mm sieve	> 0.48 55.0 to 59.0 > 90 < 2.0	g/cm³ % %	
Apparent Density K (wear) Factor Sieve Analysis 0.063mm sieve 0.25mm sieve Viscosity	> 0.48 55.0 to 59.0 > 90 < 2.0 73.0 to 86.0	g/cm ³ % % cm ³ /g	
Apparent Density K (wear) Factor Sieve Analysis 0.063mm sieve 0.25mm sieve Viscosity Volatile Matter	> 0.48 55.0 to 59.0 > 90 < 2.0 73.0 to 86.0 < 0.40	g/cm³ % % cm³/g %	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

%

Recommended distributors for this material

Whiteness - after 10min (160°C)

Susheng Import & Export Trading Co.,Ltd.

> 70

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

