

RheTech Polypropylene GC30P200-00

Polypropylene Copolymer

RheTech, Inc.

Message:

30% Glass Fiber Reinforced, Chemically Coupled Non-UV, Polypropylene Copolymer, Natural.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Copolymer Chemical coupling		
Appearance	Natural color		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	74		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	65.5	MPa	ASTM D638
Flexural Modulus	4410	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	200	J/m	ASTM D256
Dart Drop Impact	1.81	J	ASTM D5420
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	154	°C	ASTM D648
1.8 MPa, not annealed	138	°C	ASTM D648
Injection	Nominal Value	Unit	Test Method
Drying Temperature	65.6 - 82.2	°C	
Drying Time	1.0 - 2.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	204 - 232	°C	
Middle Temperature	210 - 238	°C	
Front Temperature	216 - 243	°C	
Nozzle Temperature	221 - 232	°C	
Mold Temperature	26.7 - 48.9	°C	
Injection Pressure	2.76 - 10.3	MPa	
Holding Pressure	2.07 - 8.27	MPa	

Back Pressure

0.345 - 1.03

MPa

Injection instructions

Injection Speed: Variable - Application Dependant Screw RPM: Recovery 3 seconds before mold opens Cycle Time: Wall Thickness Dependant

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

