

MAXATEL® AH500TF20-NC010

Acetal (POM) Homopolymer

Pier One Polymers, Inc.

Message:

MAXATEL®AH500TF20-NC010 is a polyoxymethylene (POM) homopolymer material. This product is available in North America and is processed by injection molding.

MAXATEL®The main features of the AH500TF20-NC010 are:

Homopolymer

Lubrication

General Information			
Additive	PTFE lubricant (20%)		
Features	Homopolymer		
	Lubrication		
Appearance	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.54	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/1.05 kg)	4.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	55.2	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	12	%	ASTM D638
Flexural Modulus (23°C)	3100	MPa	ASTM D790
Flexural Strength (23°C)	96.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	48	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	99.0	°C	ASTM D648
Peak Melting Temperature	177	°C	ASTM D3418
Injection	Nominal Value	Unit	
Drying Temperature	79	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	195 - 215	°C	
Mold Temperature	40 - 60	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

