

LNP™ LUBRICOMP™ OCP36 compound

Polyphenylene Sulfide

SABIC Innovative Plastics

Message:

LNP LUBRICOMP OCP36 is a compound based on Polyphenylene Sulfide resin containing Carbon Fiber, Lubricants, Bearing Grade. Added features of this material include: Internally Lubricated, Electrically Conductive.

Also known as: LNP* LUBRICOMP* Compound O-BG

Product reorder name: OCP36

General Information			
Filler / Reinforcement	Carbon fiber reinforced material		
Additive	Lubricant		
Features	Conductivity		
	Lubrication		
Uses	Bearing		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.51	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow: 24 hours	0.20	%	ASTM D955
Transverse flow: 24 hours	0.40 - 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	18100	MPa	ASTM D638
Tensile Strength (Break)	158	MPa	ASTM D638
Tensile Elongation (Break)	1.6	%	ASTM D638
Flexural Modulus	19900	MPa	ASTM D790
Flexural Strength	241	MPa	ASTM D790
Coefficient of Friction			ASTM D3702 Modified
With self-dynamics	0.47		ASTM D3702 Modified
With Self-Static	0.33		ASTM D3702 Modified
Wear Factor - Washer	24.0	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	53	J/m	ASTM D256
Unnotched Izod Impact (23°C)	490	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	260	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2	ohms	ASTM D257
Injection	Nominal Value	Unit	

Drying Temperature	121 - 149	°C
Drying Time	4.0	hr
Rear Temperature	304 - 316	°C
Middle Temperature	321 - 332	°C
Front Temperature	332 - 343	°C
Processing (Melt) Temp	316 - 321	°C
Mold Temperature	138 - 166	°C
Back Pressure	0.172 - 0.344	MPa
Screw Speed	30 - 60	rpm
NOTE		

1. 50 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

