

ACCUTECH™ SAN930G40L

Styrene Acrylonitrile
ACLO Compounders Inc.

Message:

ACCUTECH™ SAN930G40L is a Styrene Acrylonitrile (SAN) product filled with 40% glass fiber. It is available in North America.

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	2.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.10	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6900	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	95.0	MPa	
Break	95.0	MPa	
Tensile Elongation			ASTM D638
Yield	2.0	%	
Break	3.0	%	
Flexural Modulus	12500	MPa	ASTM D790
Flexural Strength	133	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	46	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	102	°C	
1.8 MPa, Unannealed	98.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

