

Grilamid® XE 4188 nat

Polyamide 612

EMS-GRIVORY

Message:

Grilamid® XE 4188 nat is a Polyamide 612 (Nylon 612) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for extrusion.

Important attributes of Grilamid® XE 4188 nat are:

- Flame Rated
- Chemical Resistant
- Good UV Resistance
- Heat Resistant
- High Viscosity
- Typical applications include:
 - Automotive
 - Electrical/Electronic Applications
 - Hose/Tubing
 - Outdoor Applications
 - Wire & Cable

General Information				
Features		Alcohol Resistant		
		Good UV Resistance		
		High Heat Resistance		
		High Impact Resistance		
		High Viscosity		
		Hydrolysis Resistant		
Uses		Automotive Applications		
		Electrical/Electronic Applications		
		Hydraulic Applications		
		Outdoor Applications		
		Pneumatic Applications		
		Tubing		
		Wire & Cable Applications		
Appearance		Natural Color		
Forms		Granules		
Processing Method		Extrusion		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.04	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.40	--	%	
Flow	3.0	--	%	
Water Absorption				ISO 62

Saturation, 23°C	2.7	--	%	
Equilibrium, 23°C, 50% RH	1.2	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	100	70.0	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	1800	1300	MPa	ISO 527-2
Tensile Stress (Yield)	50.0	45.0	MPa	ISO 527-2
Tensile Strain (Yield)	5.0	20	%	ISO 527-2
Nominal Tensile Strain at Break	> 50	> 50	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	12	12	kJ/m ²	
23°C	50	90	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		
23°C	No Break	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	120	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	50.0	--	°C	ISO 75-2/A
Melting Temperature ¹	218	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	1.6E-4	--	cm/cm/°C	
Transverse	1.1E-4	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+10	ohms	IEC 60093
Volume Resistivity	1.0E+10	1.0E+10	ohms·cm	IEC 60093
Electric Strength	38	38	kV/mm	IEC 60243-1
Comparative Tracking Index	--	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification (0.800 mm)	HB	--		IEC 60695-11-10, -20
Additional Information	Dry	Conditioned		Test Method
ISO Type	PA612, EH, 18-020	--		ISO 1874
NOTE				
1.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT