

NaturePlast NP DU 201

Polyamide 610

NaturePlast

Message:

The R&D progress allows today to produce some of the conventional polymers partially or totally from vegetable resources and no longer from fossil resources.

BioPA grades commercialized by NaturePlast have the same properties as the conventional PA and can be transformed on plastic processing standard equipments.

Markets: automotive, technical parts, packaging, textiles, etc.

Properties

Properties similar to oil based PA.

Processing easiness.

Recyclable in existing PA streams.

| General Information | | | |
|----------------------------------|----------------------------|--------------------|-------------|
| Features | Good Processability | | |
| | Recyclable Material | | |
| | Renewable Resource Content | | |
| Uses | Automotive Applications | | |
| | Engineering Parts | | |
| | Packaging | | |
| | Textile Applications | | |
| Forms | Pellets | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.06 | g/cm ³ | ISO 1183 |
| Viscosity Number | 160 | cm ³ /g | ISO 307 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus | 2100 | MPa | ISO 527-2 |
| Tensile Strain (Break) | > 50 | % | ISO 527-2 |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Unnotched Impact Strength | No Break | | ISO 179 |
| Thermal | Nominal Value | Unit | Test Method |
| Vicat Softening Temperature | 196 | °C | ISO 306/B |
| Additional Information | Nominal Value | Unit | Test Method |
| Biobased Content | 63 | % | ASTM D6866 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

