# Edgetek™ PS-20GF/000 NATURAL

## Polybutylene Terephthalate

## PolyOne Corporation

#### Message:

Edgetek<sup>™</sup> PS-20GF/000 NATURAL is a Polybutylene Terephthalate (PBT) product filled with 20% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Applications of Edgetek<sup>™</sup> PS-20GF/000 NATURAL include appliances, automotive, consumer goods, engineering/industrial parts and food contact applications. Characteristics include: Chemical Resistant Crystalline Heat Resistant

General Information					
Filler / Reinforcement	Glass Fiber,20% Filler by Weight				
Features	Good Chemical Resistance				
	High Heat Resistance				
	Semi Crystalline				
Uses	Appliance Components				
	Appliances				
	Automotive Applications				
	Consumer Applications				
	Housings				
	Industrial Applications				
	Structural Parts				
Agency Ratings	FDA Unspecified Rating				
Forms	Pellets				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.45	g/cm³	ASTM D792		
Molding Shrinkage			ASTM D955		
Flow : 3.18 mm	0.30 to 0.50	%			
Across Flow : 3.18 mm	1.3 to 1.5	%			
Mechanical	Nominal Value	Unit	Test Method		
Tensile Modulus <sup>1</sup>	6760	MPa	ASTM D638		
Tensile Strength <sup>2</sup> (Break)	96.5	MPa	ASTM D638		
Tensile Elongation (Break)	3.0 to 5.0	%	ASTM D638		
Flexural Modulus <sup>3</sup>	6000	MPa	ASTM D790		
Flexural Strength <sup>4</sup>	165	MPa	ASTM D790		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact	59	J/m	ASTM D256		
Thermal	Nominal Value	Unit	Test Method		

Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	219	°C	
1.8 MPa, Unannealed	182	°C	
NOTE			
1.	5.1 mm/min		
2.	5.1 mm/min		
3.	1.3 mm/min		
4.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

