

LNP™ COLORCOMP™ EX14001 compound

Polyether Imide
SABIC Innovative Plastics Europe

Message:

LNP COLORCOMP EX14001 is a compound based on Polyetherimide resin. Added Features include: Custom Color.

Also known as: LNP* COLORCOMP* Compound EX14001

Product reorder name: EX14001

General Information			
RoHS Compliance	RoHS Compliant		
Appearance	Colors Available		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.27	g/cm ³	ISO 1183
Molding Shrinkage - Flow	0.60	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3200	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	105	MPa	
Break	85.0	MPa	
Tensile Strain			ISO 527-2/50
Yield	6.0	%	
Break	60	%	
Flexural Modulus ¹	3300	MPa	ISO 178
Flexural Stress	160	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ² (23°C)	5.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ³ (23°C)	No Break		ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁴ (1.8 MPa, Unannealed, 64.0 mm Span)	190	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	150	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	80.0 to 120	°C	
Rear Temperature	340 to 395	°C	
Middle Temperature	350 to 405	°C	
Front Temperature	360 to 415	°C	
Nozzle Temperature	350 to 405	°C	
Processing (Melt) Temp	370 to 410	°C	

Mold Temperature	140 to 180	°C
NOTE		
1.	2.0 mm/min	
2.	80*10*4	
3.	80*10*4	
4.	80*10*4 mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

