

Petrothene® GA574189X02

Linear Low Density Polyethylene

LyondellBasell Industries

Message:

Petrothene GA574189X02 exhibits excellent flow and impact with good stiffness. Typical applications include lids, closures, containers, housewares and medical items.

Without exception, all potential activities for applications in the pharmaceutical, medical device, laboratory and diagnostics area have to be discussed with the relevant Technical (P & AD) and Business contacts first.

To discuss a medical/pharmaceutical application please contact: your local Distributor or your local LyondellBasell contact.

General Information		
Features	Rigid, good	
	Impact resistance, good	
	Good liquidity	
Uses	Power/other tools	
	Cover	
	Shield	
	Household goods	
	Container	
	Outdoor application	
	Shell	
	Medical/nursing supplies	
Processing Method	Injection molding	
Physical	Nominal Value	Unit
Density (23°C)	0.926	g/cm ³
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	50	g/10 min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 1342475533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT