

NEXUS ABS ABSFR1

Acrylonitrile Butadiene Styrene
Nexus Resin Group, LLC.

Message:
Molding Grade ABSFR

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
UL File Number	E205256		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	6.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2170	MPa	ASTM D638
Tensile Strength (Yield)	36.5	MPa	ASTM D638
Flexural Modulus	2240	MPa	ASTM D790
Flexural Strength (Yield)	64.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	150	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.18 mm)	75.6	°C	ASTM D648
Flammability	Nominal Value	Test Method	
Flame Rating (1.57 mm)	V-0	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	76.7 to 87.8	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.15	%	
Rear Temperature	149 to 182	°C	
Middle Temperature	177 to 204	°C	
Front Temperature	191 to 232	°C	
Nozzle Temperature	191 to 232	°C	
Processing (Melt) Temp	191 to 232	°C	
Mold Temperature	48.9 to 76.7	°C	
Back Pressure	0.172 to 0.689	MPa	
Screw Speed	25 to 75	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

