

SLOVAMID® 6 GF 5 T 20 FRG 2

Polyamide 6

Plastcom

Message:

PA 6 for injection moulding, with halogen free flame retardant based on polyphosphate. Good anisotrophi shinking. Application for the electrical industry: protectors, coil forms, covers, terminals. Delivered in natural mode and in the full RAL colour scale.

General Information			
Filler / Reinforcement	Glass Fiber,5.0% Filler by Weight		
	Talc,20% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
	Halogen Free		
Uses	Electrical/Electronic Applications		
Appearance	Colors Available		
	Natural Color		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	PA 6		
Physical	Nominal Value	Unit	Test Method
Density	1.35	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.0	g/10 min	ISO 1133
Molding Shrinkage			STM 64 0808
Across Flow	1.0	%	
Flow	0.60	%	
Water Content	0.15	%	ISO 960
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6800	MPa	ISO 527-2
Tensile Stress (Yield)	90.0	MPa	ISO 527-2
Tensile Strain (Yield)	2.5	%	ISO 527-2
Flexural Modulus	5200	MPa	ISO 178
Flexural Stress	120	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-20°C	4.0	kJ/m²	
23°C	5.0	kJ/m²	
Charpy Unnotched Impact Strength			ISO 179
-20°C	20	kJ/m²	

23°C	20	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	200	°C	ISO 75-2/B
Vicat Softening Temperature	200	°C	ISO 306/B
Melting Temperature (DSC)	220	°C	ISO 3146
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-2		UL 94
Glow Wire Ignition Temperature	960	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	70.0 to 90.0	°C	
Injection Pressure	70.0 to 120	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

