

# Makrolon® 2256

Polycarbonate

Covestro - Polycarbonates

## Message:

MVR (300 °C/1.2 kg) 34 cm<sup>3</sup>/10 min; food contact quality; low viscosity; easy release; injection molding - melt temperature 280 - 320 °C; available in transparent, translucent and opaque colors

General Information			
Features	Food Contact Acceptable Good Mold Release Low Viscosity		
RoHS Compliance	RoHS Compliant		
Appearance	Clear/Transparent Colors Available Opaque Translucent		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.19	g/cm <sup>3</sup>	ISO 1183
Apparent Density <sup>1</sup>	0.66	g/cm <sup>3</sup>	ISO 60
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	37	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	34.0	cm <sup>3</sup> /10min	ISO 1133
Molding Shrinkage			
Across Flow	0.50 to 0.70	%	ISO 2577
Flow	0.50 to 0.70	%	ISO 2577
Across Flow : 2.00 mm <sup>2</sup>	0.65	%	ISO 294-4
Flow : 2.00 mm <sup>3</sup>	0.65	%	ISO 294-4
Water Absorption			ISO 62
Saturation, 23°C	0.30	%	
Equilibrium, 23°C, 50% RH	0.12	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	115	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2400	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield, 23°C	65.0	MPa	
Break, 23°C	60.0	MPa	
Tensile Strain			ISO 527-2/50

Yield, 23°C	6.0	%	
Break, 23°C	130	%	
Nominal Tensile Strain at Break (23°C)	> 50	%	ISO 527-2/50
Tensile Creep Modulus			ISO 899-1
1 hr	2200	MPa	
1000 hr	1900	MPa	
Flexural Modulus <sup>4</sup> (23°C)	2350	MPa	ISO 178
Flexural Stress <sup>5</sup>			ISO 178
3.5% Strain, 23°C	73.0	MPa	
23°C	97.0	MPa	
Flexural Strain at Flexural Strength (23°C) <sup>6</sup>	7.1	%	ISO 178
Gas Permeation			ISO 2556
Carbon Dioxide : 23°C, 25.4 µm	18900	cm <sup>3</sup> /m <sup>2</sup> /bar/24 hr	
Carbon Dioxide : 23°C, 100.0 µm	4500	cm <sup>3</sup> /m <sup>2</sup> /bar/24 hr	
Nitrogen : 23°C, 25.4 µm	630	cm <sup>3</sup> /m <sup>2</sup> /bar/24 hr	
Nitrogen : 23°C, 100.0 µm	150	cm <sup>3</sup> /m <sup>2</sup> /bar/24 hr	
Oxygen : 23°C, 25.4 µm	3150	cm <sup>3</sup> /m <sup>2</sup> /bar/24 hr	
Oxygen : 23°C, 100.0 µm	750	cm <sup>3</sup> /m <sup>2</sup> /bar/24 hr	
Application of Flame from Small Burner - Method K and F (2.00 mm)	K1, F1		DIN 53438-1, -3
Burning Rate - US-FMVSS (> 1.00 mm)	passed		ISO 3795
Flash Ignition Temperature	480	°C	ASTM D1929
Needle Flame Test			IEC 60695-11-5
Method F : 1.50 mm	1.0	min	
Method F : 2.00 mm	2.0	min	
Method F : 3.00 mm	2.0	min	
Method K : 1.50 mm	0.1	min	
Method K : 2.00 mm	0.1	min	
Method K : 3.00 mm	0.2	min	
Self Ignition Temperature	550	°C	ASTM D1929
Electrolytical Corrosion (23°C)	A1		IEC 60426
ISO Shortname	ISO 7391-PC,MR,(,,)-24-9		
<b>Films</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Water Vapor Transmission Rate (23°C, 85% RH, 100 µm)	15	g/m <sup>2</sup> /24 hr	ISO 15106-1
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Charpy Notched Impact Strength <sup>7</sup>			ISO 7391
-30°C, Complete Break	12	kJ/m <sup>2</sup>	
23°C, Partial Break	55	kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-60°C	No Break		
-30°C	No Break		
23°C	No Break		

Notched Izod Impact Strength <sup>8</sup>			ISO 7391
-30°C, Complete Break	12	kJ/m <sup>2</sup>	
23°C, Partial Break	55	kJ/m <sup>2</sup>	
Multi-Axial Instrumented Impact Energy			ISO 6603-2
-30°C	60.0	J	
23°C	55.0	J	
Multi-Axial Instrumented Impact Peak Force			ISO 6603-2
-30°C	5900	N	
23°C	4900	N	
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Heat Deflection Temperature			
0.45 MPa, Unannealed	137	°C	ISO 75-2/B
1.8 MPa, Unannealed	124	°C	ISO 75-2/A
Glass Transition Temperature <sup>9</sup>	145	°C	ISO 11357-2
Vicat Softening Temperature			
--	145	°C	ISO 306/B50
--	146	°C	ISO 306/B120
Ball Pressure Test (136°C)	Pass		IEC 60695-10-2
CLTE			
Flow : 23 to 55°C	6.5E-5	cm/cm/°C	
Transverse : 23 to 55°C	6.5E-5	cm/cm/°C	
Thermal Conductivity <sup>10</sup> (23°C)	0.20	W/m/K	ISO 8302
<b>Electrical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+16	ohms·cm	IEC 60093
Electric Strength (23°C, 1.00 mm)	34	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
23°C, 100 Hz	3.10		
23°C, 1 MHz	3.00		
Dissipation Factor			IEC 60250
23°C, 100 Hz	5.0E-4		
23°C, 1 MHz	9.0E-3		
Comparative Tracking Index			IEC 60112
Solution A	250	V	
Solution B	125	V	
<b>Flammability</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Glow Wire Flammability Index			IEC 60695-2-12
0.750 mm	850	°C	
1.50 mm	875	°C	
3.00 mm	930	°C	
Glow Wire Ignition Temperature			IEC 60695-2-13

0.750 mm	875	°C	
1.50 mm	875	°C	
3.00 mm	875	°C	
Oxygen Index <sup>11</sup>	28	%	ISO 4589-2
Optical	Nominal Value	Unit	Test Method
Refractive Index <sup>12</sup>	1.586		ISO 489
Transmittance			ISO 13468-2
1000 μm	89.0	%	
2000 μm	89.0	%	
3000 μm	88.0	%	
4000 μm	87.0	%	
Haze (3000 μm)	< 0.80	%	ISO 14782

#### NOTE

1. Pellets
2. 60x60x2 mm, 500 bar
3. 60x60x2 mm, 500 bar
4. 2.0 mm/min
5. 2.0 mm/min
6. 2 mm/min
7. Based on ISO 179-1eA, 3 mm
8. Based on ISO 180-A, 3 mm
9. 10°C/min
10. Cross-flow
11. Procedure A
12. Method A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

