

Desmopan® DP 9662DU

Thermoplastic Polyurethane Elastomer (Polyether)

Covestro - PUR

Message:

Extrusion- and injection molding grade; with special UV stabilizers; transparent up to 6 mm wall thickness; very good hydrolysis and microbial resistance;
Application; Ski boot shells; Hoses, non-reinforced

General Information	
Additive	UV Stabilizer
Features	Hydrolysis Resistant
	Microbe Resistant
Uses	Hose
	Sporting Goods
RoHS Compliance	RoHS Compliant
Appearance	Clear/Transparent
Processing Method	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.18	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore A, 23°C	97		
Shore D, 23°C	62		
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress ¹			DIN 53504
Break, 23°C	52.7	MPa	
10% Strain, 23°C	12.3	MPa	
50% Strain, 23°C	20.7	MPa	
100% Strain, 23°C	26.0	MPa	
300% Strain, 23°C	40.1	MPa	
Tensile Strain ² (Break, 23°C)	350	%	DIN 53504
Flexural Modulus ³ (23°C)	185	MPa	ISO 178
Abrasion Resistance (23°C)	20.0	mm ³	ISO 4649-A
Tensile Storage Modulus			ISO 6721-1,-4
-20°C	2.53	GPa	
20°C	0.643	GPa	
60°C	0.187	GPa	

Impact Resilience (23°C)	31	%	ISO 4662
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ⁴ (23°C)	98	kN/m	ISO 34-1
Compression Set			ISO 815
23°C, 72 hr	59	%	
70°C, 24 hr	87	%	
Injection	Nominal Value	Unit	
Drying Temperature	< 110	°C	
Processing (Melt) Temp	220 to 235	°C	
Mold Temperature	40.0 to 60.0	°C	
Extrusion	Nominal Value	Unit	
Drying Temperature	< 110	°C	
Melt Temperature	205 to 235	°C	
NOTE			
1.	200 mm/min		
2.	200 mm/min		
3.	2.0 mm/min		
4.	500 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

