

VAMPLEN 0024 V2 LBC

Polypropylene Homopolymer
Vamp Tech

Message:

UL 94 V2 at 1,6 mm, homopolymer, halogen free, good dimensional stability and thermal resistance, GWIT 775/1-2, RoHS.

General Information			
UL YellowCard	E140692-223058		
Features	Good Dimensional Stability		
	Halogen Free		
	High Heat Resistance		
	Homopolymer		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	1.2	%	
Across Flow	1.2	%	
Water Absorption (Saturation)	0.020	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1500	MPa	ASTM D638
Tensile Strength (Yield)	20.0	MPa	ASTM D638
Tensile Elongation (Break)	> 100	%	ASTM D638
Flexural Modulus	1900	MPa	ASTM D790
Flexural Strength	35.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	2.5	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength	25	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	70.0	°C	ASTM D648A
Vicat Softening Temperature	100	°C	ASTM D1525 ¹
RTI Elec	110	°C	UL 746
RTI Imp	110	°C	UL 746
RTI Str	110	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	V-2		

1.60 mm	V-2		
3.20 mm	V-2		
Glow Wire Flammability Index (1.00 to 2.00 mm)	850	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (1.00 to 2.00 mm)	775	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	70.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	210	°C	
Mold Temperature	60.0	°C	
NOTE			

1.

Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT