

MARPOL® EMA 2-20

Ethylene Methyl Acrylate Copolymer

Marco Polo International, Inc.

Message:

Processing: Extrusion and Molding

Applications: Extruded embossed sheets, food and medical applications, packaging bottles, ampoule trays, caps and closures.

MARPOL® GPPS 1.5 grade can - in principle - be used in food contact applications in the USA (FDA) and in Canada (HBP). Migration or use limitations may apply.

General Information			
Features	Copolymer		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR)	2.0	g/10 min	ASTM D1238
Methyl Acrylate Content	20.0	wt%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	35		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-99.0	°C	ASTM D746
Vicat Softening Temperature	122	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT