

Domamid HT™ 7750R15F4H3 Bk-598

Polyamide 66
Technical Polymers, LLC

Message:
PA66, 15% Glass Fiber, Flame Retardant, Enhanced Heat Stabilization, Black
Processing Method: Injection Molding

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 15% filler by weight		
Features	Good Heat Resistance		
	Flame retardancy		
Appearance	Black		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.30	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	6500	MPa	ISO 527-2
Tensile Stress (23°C)	100	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.0 - 4.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.5	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	260	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+14	ohms · cm	ISO 3915
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	75 - 80	°C	
Drying Time	3.0 - 4.0	hr	
Processing (Melt) Temp	280 - 300	°C	
Mold Temperature	65 - 90	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

