

Celstran® TPU-GF60-01

Thermoplastic Polyurethane Elastomer

Celanese Corporation

Message:

60% long strand glass fiber reinforced thermoplastic polyurethane

General Information			
UL YellowCard	E113269-237810		
Filler / Reinforcement	Long glass fiber, 60% filler by weight		
RoHS Compliance	Contact manufacturer		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.76	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			ASTM D955
Flow	0.050 - 0.10	%	ASTM D955
Transverse flow	0.050 - 0.10	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
23°C	19900	MPa	ASTM D638
--	18700	MPa	ISO 527-2/1A/1
Tensile Strength			
Fracture, 23°C	259	MPa	ASTM D638
Fracture	240	MPa	ISO 527-2/1A/5
Tensile Elongation			
Fracture, 23°C	1.7	%	ASTM D638
Fracture	1.8	%	ISO 527-2/1A/5
Flexural Modulus (23°C)	18300	MPa	ISO 178
Flexural Stress (23°C)	420	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	66	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	102	°C	ASTM D648, ISO 75-2/A
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.050	%	
Hopper Temperature	70.0 - 80.0	°C	
Rear Temperature	240 - 250	°C	
Middle Temperature	245 - 255	°C	
Front Temperature	245 - 260	°C	

Nozzle Temperature	245 - 260	°C
Processing (Melt) Temp	245 - 260	°C
Mold Temperature	70.0 - 90.0	°C

Injection instructions

Manifold Temperature: 250 to 265°CZone 4 Temperature: 245 to 260°CFeed Temperature: 20 to 50°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

