## Hy-Vin® VX390

# Flexible Polyvinyl Chloride INEOS Compounds

#### Message:

Hy-Vin® VX390 is a Flexible Polyvinyl Chloride material. It is available in Europe. Important attributes of Hy-Vin® VX390 are:
Good Flexibility
Good Processability

| General Information                    |                  |       |              |
|--|------------------|-------|--------------|
| Features                               | General Purpose  |       |              |
|  | Good Flexibility |       |              |
|  | Good Moldability |       |              |
|  |                  |       |              |
| Uses                                   | General Purpose  |       |              |
| Appearance                             | Colors Available |       |              |
| Forms                                  | Pellets          |       |              |
| Physical                               | Nominal Value    | Unit  | Test Method  |
| Specific Gravity                       | 1.36             | g/cm³ | BS 2782      |
| Water Absorption (Saturation)          | 0.25             | %     | BS 2782 430A |
| Hardness                               | Nominal Value    | Unit  | Test Method  |
| Shore Hardness (Shore A, 15 sec, 23°C) | 90               |       | BS 2782      |
| BS Softness                            | 17               | ۰     | BS 2782      |
| Cold Bend                              | < -20            | °C    | BS 2782      |
| Cold Flexibility                       | -10              | °C    | BS 2782      |
| Extrusion                              | Nominal Value    | Unit  |              |
| Cylinder Zone 1 Temp.                  | 170              | °C    |              |
| Cylinder Zone 2 Temp.                  | 170              | °C    |              |
| Cylinder Zone 3 Temp.                  | 170              | °C    |              |
| Die Temperature                        | 170              | °C    |              |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

