

Akulon® S223-EH

Polyamide 66
DSM Engineering Plastics

Message:

Akulon® S223-EH is a Polyamide 66 (Nylon 66) material. It is available in Asia Pacific or Europe.
Important attributes of Akulon® S223-EH are:
Flame Rated
Heat Stabilizer
Medium Viscosity

General Information		
UL YellowCard	E43392-235159	E47960-240109
Additive	Heat Stabilizer	
Features	Heat Stabilized	
	Medium-low Viscosity	

Multi-Point Data	Isochronous Stress vs. Strain (ISO 11403-1)			
	Isothermal Stress vs. Strain (ISO 11403-1)			
	Secant Modulus vs. Strain (ISO 11403-1)			
	Shear Modulus vs. Temperature (ISO 11403-1)			
	Specific Heat vs. Temperature (ISO 11403-2)			
	Specific Volume vs Temperature (ISO 11403-2)			
	Viscosity vs. Shear Rate (ISO 11403-2)			

Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.6	--	%	
Flow	1.6	--	%	
Water Absorption				ISO 62
Saturation, 23°C	8.5	--	%	
Equilibrium, 23°C, 50% RH	2.3	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	3500	1500	MPa	ISO 527-2
Tensile Stress (Yield)	95.0	60.0	MPa	ISO 527-2
Tensile Strain (Yield)	3.5	20	%	ISO 527-2
Nominal Tensile Strain at Break	25	> 50	%	ISO 527-2
Flexural Modulus	2800	--	MPa	ISO 178
Flexural Stress	125	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method

Charpy Notched Impact Strength				ISO 179/1eA
-30°C	6.0	6.0	kJ/m ²	
23°C	6.0	12	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		
23°C	No Break	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	225	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	80.0	--	°C	ISO 75-2/A
Melting Temperature ¹	260	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	1.0E-4	--	cm/cm/°C	
Transverse	1.0E-4	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+14	1.0E+12	ohms·cm	IEC 60093
Electric Strength	25	20	kV/mm	IEC 60243-1
Relative Permittivity				IEC 60250
100 Hz	3.40	10.0		
1 MHz	3.20	4.00		
Dissipation Factor				IEC 60250
100 Hz	0.013	0.30		
1 MHz	0.020	0.10		
Comparative Tracking Index	600	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification				IEC 60695-11-10, -20
1.50 mm	V-2	--		
0.710 mm	HB	--		
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	4.0 to 8.0		hr	
Rear Temperature	265 to 285		°C	
Middle Temperature	275 to 290		°C	
Front Temperature	280 to 295		°C	
Nozzle Temperature	280 to 290		°C	
Processing (Melt) Temp	270 to 295		°C	
Mold Temperature	50.0 to 80.0		°C	
Injection Rate	Moderate-Fast			

Back Pressure	3.00 to 10.0	MPa
Screw Compression Ratio	2.5:1.0	
NOTE		
1.	10°C/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

