

Wah Hong BMC BUG-3101C Electrical

Thermoset, Unspecified

Wah Hong Industrial Corp.

Message:

BMC material for all kinds of electric and electronic parts, like Breaker, Non-Fuse Switches, and Oven parts. Electric BMC with UL94 V-0, good creep resistance, good mechanical strength and electrical property.

General Information			
Filler / Reinforcement	Filler		
Features	Good Creep Resistance		
	Good Electrical Properties		
	Good Strength		
Uses	Electrical Parts		
	Electrical/Electronic Applications		
	Switches		
Forms	BMC - Bulk Molding Compound		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.85 to 1.91	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.020 to 0.040	%	ASTM D955
Water Absorption (24 hr)	< 0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	29.4 to 49.0	MPa	ASTM D638
Flexural Modulus	10800 to 14700	MPa	ASTM D790
Flexural Strength	78.5 to 118	MPa	ASTM D790
Compressive Strength	137 to 157	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	> 200	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	> 220	°C	ASTM D648
Melting Temperature	115	°C	DSC
Electrical	Nominal Value	Unit	Test Method
Arc Resistance	> 180	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Additional Information	Nominal Value	Unit	
Cure Time (140°C)	40.0 to 50.0	sec	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

