

Rilsamid® AECHVO

Polyamide 12

Arkema

Message:

Rilsamid ® AECHVO is a natural polyamide 12. This grade is designed for cable coating but is also suitable for extrusion.

MAIN APPLICATIONS

Wire sheathing.

General Information			
Uses	Cable Jacketing		
	Wire & Cable Applications		
Appearance	Natural Color		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.01	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (235°C/5.0 kg)	45.0	cm ³ /10min	ISO 11357
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 15 sec)	73		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2
Yield	38.0	MPa	
Break	70.0	MPa	
Tensile Strain			ISO 527-2
Yield	6.0	%	
Break	> 200	%	
Flexural Modulus	1200	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	6.0	kJ/m ²	
23°C	7.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	178	°C	ISO 11357-3
Additional Information	Nominal Value		Test Method
ISO Shortname	PA12, K, 18-010		ISO 1874
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0	°C	

Drying Time	4.0 to 8.0	hr
Melt Temperature	240 to 260	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

