

BCC Resins BC 6126

Epoxy; Epoxide

BCC Products Inc.

Message:

BC 6126 is a gray, low toxicity, aluminum filled, epoxy surface coat. This thixotropic resin system provides excellent surface duplication along with vertical coverage to 1/16" thickness. This heat resistant system may be used at room temperature without post-curing. For use above 150°F a post-cure is required. Post cure for applications requiring temperatures above 150°F can be accomplished in an oven or in use by a gradual heat rise; 2 hours @ 150°F, plus 2 hours @ 250°F, plus 2 hours at 300°F. BC 6126 can afford consistent use to 300°F if required. BC 6126 was engineered to replace VCHD and MDA systems while retaining excellent heat resistance. Typical uses include constructing vacuum form tools, Injection and compression molds, RTM and RIM molds, and matched dies.

General Information			
Filler / Reinforcement	Aluminum		
Features	High Heat Resistance		
	Low Toxicity		
Uses	Coating Applications		
Appearance	Grey		
Forms	Paste		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.47	g/cm ³	ASTM D792, ASTM D1505
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	90		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Ultimate)	40.0	MPa	ASTM D638
Flexural Strength (Break)	44.8	MPa	ASTM D790
Compressive Strength	193	MPa	ASTM D695
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	144	°C	ASTM D648
CLTE - Flow	4.2E-5	cm/cm/°C	ASTM D696
Thermoset	Nominal Value	Unit	
Thermoset Components			
Hardener	Mix Ratio by Weight: 10, Mix Ratio by Volume: 15		
Resin	Mix Ratio by Weight: 100, Mix Ratio by Volume: 100		
Pot Life (24°C)	45	min	
Demold Time (24°C)	720 to 960	min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

