

TRANSMARE® 35HNF50-0.001

Polypropylene Homopolymer

Transmare Compounding B.V.

Message:

TRANSMARE® 35HNF50-0.001 is a 50% bamboo fiber reinforced polypropylene homopolymer.

General Information			
Filler / Reinforcement	Bamboo Fiber, 50% filler by weight		
Features	Homopolymer		
	Updatable resources		
	Recyclable materials		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.02	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.2	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	78		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (4.00 mm)	5050	MPa	ISO 527-2/1
Tensile Stress (Break, 4.00 mm, Injection Molded)	43.0	MPa	ISO 527-2/50
Tensile Strain (Break, 4.00 mm, Injection Molded)	1.6	%	ISO 527-2/50
Flexural Modulus	4960	MPa	ISO 178
Flexural Stress	68.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1A
-40°C	2.5	kJ/m ²	ISO 179/1A
0°C	3.0	kJ/m ²	ISO 179/1A
23°C	3.4	kJ/m ²	ISO 179/1A
Charpy Unnotched Impact Strength			ISO 179/1U
-40°C	7.3	kJ/m ²	ISO 179/1U
23°C	9.2	kJ/m ²	ISO 179/1U
Notched Izod Impact (23°C)	3.6	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	9.3	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	148	°C	ISO 75-2/B

1.8 MPa, not annealed	103	°C	ISO 75-2/A
Vicat Softening Temperature	163	°C	ISO 306/A
Injection	Nominal Value	Unit	
Rear Temperature	150	°C	
Middle Temperature	160	°C	
Front Temperature	175	°C	
Nozzle Temperature	180	°C	
Mold Temperature	40.0 - 60.0	°C	
Injection Rate	Moderate		
Injection instructions			

In specific cases pre-drying of this material might be required.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT