

Grilamid® XE 4181 nat

Polyamide 1010

EMS-GRIVORY

Message:

Grilamid® XE 4181 nat is a Polyamide 1010 (Nylon 1010) material. It is available in Asia Pacific, Europe, or North America for extrusion.

Important attributes of Grilamid® XE 4181 nat are:

- Flame Rated
- Eco-Friendly/Green
- Good Flexibility
- Good UV Resistance
- Heat Resistant
- Typical applications include:
 - Automotive
 - Electrical/Electronic Applications
 - Hose/Tubing
 - Outdoor Applications
 - Wire & Cable

General Information				
Features		Good Flexibility		
		Good UV Resistance		
		High Heat Resistance		
		High Impact Resistance		
		High Viscosity		
		Renewable Resource Content		
Uses		Automotive Applications		
		Electrical/Electronic Applications		
		Hydraulic Applications		
		Outdoor Applications		
		Pneumatic Applications		
		Tubing		
		Wire & Cable Applications		
Appearance		Natural Color		
Forms		Granules		
Processing Method		Extrusion		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.05	--	g/cm ³	ISO 1183
Water Absorption				ISO 62
Saturation, 23°C	1.3	--	%	
Equilibrium, 23°C, 50% RH	0.70	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method

Tensile Modulus	800	600	MPa	ISO 527-2
Tensile Stress (Yield)	40.0	35.0	MPa	ISO 527-2
Tensile Strain (Yield)	30	30	%	ISO 527-2
Nominal Tensile Strain at Break	> 50	> 50	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	--	55	kJ/m ²	
23°C	70 kJ/m ²	No Break		
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		
23°C	No Break	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	125	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	55.0	--	°C	ISO 75-2/A
Melting Temperature ¹	197	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	1.7E-4	--	cm/cm/°C	
Transverse	1.1E-4	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+11	ohms	IEC 60093
Volume Resistivity	1.0E+11	1.0E+10	ohms·cm	IEC 60093
Electric Strength	39	37	kV/mm	IEC 60243-1
Comparative Tracking Index	--	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification (0.800 mm)	HB	--		IEC 60695-11-10, -20
Additional Information	Dry	Conditioned		Test Method
ISO Type	PA1010-HIP, E, 24-007	--		ISO 1874
NOTE				
1.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

