

Huaxia Shenzhou FKM DS2601-1

Fluoroelastomer

Shandong Huaxia Shenzhou New Material Co., Ltd.

Message:

Fluorous rubber (FKM-DS2600), commonly called 2# rubber, is white elastomer and copolymer of VDF and hexafluoropropylene, with fluorine content of over 66%. The product processed and vulcanized by raw fluorous rubber (DS2600), featured by good mechanical property and excellent oil resistance (fuels, synthetic oils, lubricating oils) and heat resistance, is an indispensable material for modern aviation, rocket, missile, space flight, and other top technologies and industries.

Characteristic: Low Mooney viscosity, good polymer rheological properties

Application: Additives for reducing the viscosity of high Mooney rubber, O-rings, and anti-extrusion parts of synthetic products

General Information		
Features	Copolymer	
	Fuel Resistant	
	Good Corrosion Resistance	
	Good Weather Resistance	
	High Heat Resistance	
	Low Viscosity	
	Oil Resistant	
	Ozone Resistant	
	Radiation (Gamma) Resistant	
Uses	Additive	
	Aerospace Applications	
	Cable Jacketing	
	Coating Applications	
	Diaphragms	
	Gaskets	
	Piping	
	Seals	
Appearance	Transparent - Slight Yellow	
	White	
Forms	Film	
Physical	Nominal Value	Unit
Specific Gravity	1.78 to 1.83	g/cm ³
Mooney Viscosity (ML 1+10, 121°C)	10 to 29	MU
Elastomers	Nominal Value	Unit
Tensile Strength		
--	> 11.0	MPa
-- ¹	> 9.00	MPa

Tensile Elongation		
Break	> 150	%
Break ²	> 120	%
Compression Set ³ (200°C, 24 hr)	< 25	%

NOTE		
1.	Aged for 24 hr at 275°C	
2.	Aged for 24 hr at 275°C	
3.	Bisphenol AF, compression ratio 30%	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT