

ALTECH® PP-H A 2030/100 GF30

Polypropylene Homopolymer

ALBIS PLASTIC GmbH

Message:

ALTECH® PP-H A 2030/100 GF30 is a Polypropylene Homopolymer (PP Homopolymer) product filled with 30% glass fiber. It is available in Asia Pacific, Europe, or North America.

Characteristics include:

REACH Compliant

RoHS Compliant

High Stiffness

Homopolymer

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	High Stiffness		
	Homopolymer		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/21.6 kg)	3.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5200	MPa	ISO 527-2
Tensile Stress (Break)	55.0	MPa	ISO 527-2
Tensile Strain (Break)	2.0	%	ISO 527-2
Flexural Stress	75.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	12	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	138	°C	ISO 75-2/A
Vicat Softening Temperature	110	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+18	ohms · cm	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature			
Circulation Dryer	80.0 to 120	°C	
Desiccant Dryer	80.0 to 120	°C	
Drying Time			
Circulation Dryer	2.0 to 4.0	hr	

Desiccant Dryer	2.0 to 3.0	hr
Processing (Melt) Temp	200 to 270	°C
Mold Temperature	20.0 to 90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

