

PPR PA602

Polyamide 6
Premier Plastic Resins, Inc.

Message:
Nylon 6 13% Glass Fiber Reinforced Heat Stabilized Natural

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 13% filler by weight		
Additive	heat stabilizer		
Features	Thermal Stability		
Appearance	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	107	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus - Tangent	5170	MPa	ASTM D790
Flexural Strength	168	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	213	°C	ASTM D648
1.8 MPa, not annealed	193	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	71.0 - 82.0	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	238 - 282	°C	
Middle Temperature	249 - 293	°C	
Front Temperature	249 - 293	°C	
Nozzle Temperature	243 - 288	°C	
Processing (Melt) Temp	254 - 299	°C	
Mold Temperature	66.0 - 93.0	°C	
Injection Pressure	14.0 - 103	MPa	
Injection Rate	Moderate-Fast		
Holding Pressure	10.0 - 83.0	MPa	

Back Pressure	0.00 - 1.00	MPa
Cushion	6.35 - 12.7	mm
Injection instructions		

Screw Speed: Slow-ModerateDecompression: 3.81 to 7.6 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

