

Witcom PP 2012/078 Blue

Polypropylene

Witcom Engineering Plastics B.V.

Message:

Soft magnetic, metal and X-ray detectable, suitable for food contact applications

General Information			
Features	Metal Detectable		
	Compliance of Food Exposure		
Appearance	Blue		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.45	g/cm ³	ISO 1183
Molding Shrinkage - Flow (3.00 mm)	1.2 - 1.7	%	ISO 2577
Water Absorption			ISO 62
Saturated, 23°C	0.020	%	ISO 62
Equilibrium, 23°C, 50% RH	0.010	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	< 20.0	MPa	ISO 527-2
Tensile Strain (Break)	> 30	%	ISO 527-2
Flexural Modulus	2100	MPa	ISO 178
Flexural Stress	30.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	9.5	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength	No Break		ISO 180/1U
Flammability	Nominal Value		Test Method
Flame Rating (3.00 mm)	HB		ISO 1210
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.050	%	
Processing (Melt) Temp	200 - 260	°C	
Mold Temperature	40.0 - 80.0	°C	
Injection Rate	Fast		
Back Pressure	0.00 - 1.00	MPa	
Injection instructions			

Screw speed: 0.1 - 0.25 m/sInjection pressure: Keep to a minimumHold pressure: Keep to a minimum

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

