

POCAN® KU 2-7317 000000

Polybutylene Terephthalate

LANXESS GmbH

Message:

PBT, 17 % white pigments, injection molding, improved light reflection, low tendency to warp, improved impact strength

General Information			
UL YellowCard	E245249-474049		
Additive	Pigment (17%)		
Features	Low warpage		
	High reflectivity		
	Impact resistance, good		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	White		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.45	g/cm ³	ISO 1183
Apparent Density	0.90	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (260°C/2.16 kg)	18.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 2577
Vertical flow direction: 260°C, 2.00mm ¹	1.9	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.30	%	ISO 2577
Flow direction: 260°C, 2.00mm ³	1.9	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.30	%	ISO 2577
Water Absorption			ISO 62
Saturated, 23°C	0.40	%	ISO 62
Equilibrium, 23°C, 50% RH	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	40.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	15	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	2600	MPa	ISO 178/A
Flexural Stress			ISO 178/A
3.5% strain, 23°C	70.0	MPa	ISO 178/A
23°C ⁶	75.0	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	5.8	%	ISO 178/A
ISO Shortname	PBT, GHMPR, 09-020, MD17		ISO 7792
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	ISO 179/1eA
23°C	< 10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	90	kJ/m ²	ISO 179/1eU
23°C	140	kJ/m ²	ISO 179/1eU
Notched Izod Impact			ISO 180/1A
-40°C	< 10	kJ/m ²	ISO 180/1A
-30°C	< 10	kJ/m ²	ISO 180/1A
23°C	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	60	kJ/m ²	ISO 180/1U
23°C	130	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	140	°C	ISO 75-2/B
1.8 MPa, not annealed	60.0	°C	ISO 75-2/A
Vicat Softening Temperature	160	°C	ISO 306/B120
Melting Temperature ⁸	225	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow: 23 to 55°C	1.1E-4	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	1.1E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	HB		UL 94
1.60 mm	HB		UL 94
NOTE			
1.	60x60x2mm, 80°C MT, 600 bar		
2.	60x60x2mm		
3.	60x60x2mm, 80°C MT, 600 bar		
4.	60x60x2mm		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	2 mm/min		
8.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

