

Karina GRAY PVC COMPOUND

750-18/328-F-IS-BZ

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

Message:

HEAVY METAL FREE PVC COMPOUND RECOMMENDED FOR PLUGS INJECTION AND PROFILES EXTRUSION.

General Information			
Uses	Profiles		
	Reflectors		
Appearance	Grey		
Processing Method	Profile Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.39 to 1.45	g/cm ³	ASTM D792
Color	OK		ME 12
Color a	-2.08 to 0.920		ME 12
Color b	3.88 to 6.88		ME 12
Color L	72.0 to 75.0		ME 12
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	73 to 77		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 12.3	MPa	ASTM D638
Tensile Elongation (Yield)	> 250	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -24.0	°C	ASTM D746
NOTE			
1.	24 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT