

Kuraray K-Polymer SD-1000

Polyvinyl Alcohol

Kuraray Co., Ltd.

Message:

Carboxylic acid containing grades

General Information			
Features	Biodegradable		
	Water Soluble		
Forms	Granules		
Physical	Nominal Value	Unit	Test Method
Solution Viscosity ¹	2 to 3	mPa · s	JIS K6726
Volatile Matter ²	< 5.0	%	
Degree of Hydrolysis ³	83 to 88	%	
NOTE			
1.	4 % aqueous solution at 20 °C determined by Brookfield synchronized-motor rotary-type visometer		
2.	After 3 hrs drying at 105°C, Methanol content less than 3%		
3.	Saponification		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT