

DOMAMID® 66G35V0P 1001

Polyamide 66

DOMO Engineering Plastics SPA

Message:

Polyamide 66, 35% glass fiber reinforced, red phosphorous flame retardant, for injection moulding.

General Information			
Filler / Reinforcement	Glass Fiber,35% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.44	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 2577
Across Flow : 23°C, 72 hr	0.80 to 1.0	%	
Flow : 23°C, 72 hr	0.30 to 0.50	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	11000	MPa	ISO 527-2/1
Tensile Stress (Break)	160	MPa	ISO 527-2/5
Tensile Strain (Break)	2.2	%	ISO 527-2/5
Flexural Modulus ²	9000	MPa	ISO 178
Flexural Stress ³	205	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	13	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	70	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength (23°C)	12	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	65	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	250	°C	ISO 75-2/B
1.8 MPa, Unannealed	240	°C	ISO 75-2/A
Vicat Softening Temperature	250	°C	ISO 306/B50
Melting Temperature	263	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Comparative Tracking Index (Solution A)	575	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Burning Rate	< 100	mm/min	FMVSS 302
Flame Rating (0.800 mm)	V-0		UL 94

Glow Wire Flammability Index (1.00 to 3.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (1.00 to 3.00 mm)	775	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	75.0 to 85.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	270 to 290	°C	
Mold Temperature	80.0 to 100	°C	
NOTE			
1.	50% RH		
2.	2.0 mm/min		
3.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

