

Arnitel® XG5855

Thermoplastic Copolyester Elastomer
DSM Engineering Plastics

Message:

Arnitel® XG5855 is a Thermoplastic Copolyester Elastomer (TPC-ET) material. It is available in Asia Pacific, Europe, or North America for extrusion. Primary attribute of Arnitel® XG5855: Flame Rated.

General Information			
UL YellowCard	E47960-100478254		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	2.70	cm³/10min	ISO 1133
Water Absorption			ISO 62
Saturation, 23°C	0.17	%	
Equilibrium, 23°C, 50% RH	0.45	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 3 sec)	86		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	56.0	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Break	8.50	MPa	
10% Strain	3.00	MPa	
100% Strain	4.40	MPa	
Nominal Tensile Strain at Break	350	%	ISO 527-2
Thermal	Nominal Value	Unit	Test Method
Melting Temperature ¹	172	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.9E+13	ohms · cm	IEC 60093
Electric Strength	21	kV/mm	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flammability Classification (0.800 mm)	V-2		IEC 60695-11-10, -20
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

