

Capilene® G 65 F

Polypropylene Homopolymer

Carmel Olefins Ltd.

Message:

CAPILENE ® G 65 F is a polypropylene homopolymer intended for biaxially oriented polypropylene (BOPP) film applications.

CAPILENE ® G 65 F features: good processability, easy film stretchability and good mechanical properties; does not contain calcium stearate, slip and anti-blocking additives.

CAPILENE ® G 65 F is suitable for: BOPP plain or coextruded packaging films, metallizable BOPP film; extrusion and coextrusion thermoforming.

General Information			
Features	Additive Free		
	Good Processability		
	Good Stretchability		
	Homopolymer		
	Metallizable		
Uses	Bi-axially Oriented Film		
	Packaging		
Agency Ratings	EC 1907/2006 (REACH)		
Forms	Pellets		
Processing Method	Bi-axially Oriented Film		
	Coextrusion		
	Extrusion		
	Thermoforming		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.0	g/10 min	ASTM D1238, ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield ¹	33.0	MPa	ASTM D638
Yield	30.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ²	15	%	ASTM D638
Yield	13	%	ISO 527-2/50
Flexural Modulus			
--	1550	MPa	ASTM D790
-- ³	1400	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			

23°C	40	J/m	ASTM D256
23°C	3.5	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	95.0	°C	ASTM D648
0.45 MPa, Unannealed	89.0	°C	ISO 75-2/B
Vicat Softening Temperature	155	°C	ISO 306/A, ASTM D1525 ⁴
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	5.0 mm/min		
4.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

