

TOPAS® 8007F-500

Cyclic Olefin Copolymer
Polyplastics Co., Ltd.

Message:
Film grade, Improved moldability

General Information			
Features	Copolymer		
Uses	Film		
Part Marking Code (ISO 11469)	>COC<		
Physical	Nominal Value	Unit	Test Method
Density	1.01	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR)			ISO 1133
190°C/2.16 kg	2.00	cm ³ /10min	
230°C/2.16 kg	11.0	cm ³ /10min	
Water Absorption (Saturation, 23°C)	0.010	%	ISO 62
Films	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-3
MD	2100	MPa	
TD	1800	MPa	
Tensile Stress			ISO 527-3
MD : Break	55.0	MPa	
TD : Break	52.0	MPa	
Tensile Elongation			ISO 527-3
MD : Break	3.4	%	
TD : Break	3.4	%	
Water Vapor Transmission Rate (38°C, 90% RH)	0.085	g·mm/m ² /atm/24 hr	ISO 15106-3
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature ¹	78.0	°C	ISO 11357-2
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

