

APICAL 150AF019

Thermoset Polyimide

Kaneka Corporation

Message:

APICAL 150AF019 is a Thermoset Polyimide material. It is available in North America.

Important attributes of APICAL 150AF019 are:

Flame Rated

Chemical Resistant

Flame Retardant

Good Sealability

Moisture Resistant

Typical application of APICAL 150AF019: Film

General Information			
UL YellowCard	E48854-241073		
Features	Flame Retardant		
	Good Chemical Resistance		
	Good Heat Seal		
	Moisture Resistant		
Uses	Film		
Appearance	Natural Color		
Forms	Sheet		
Physical	Nominal Value	Unit	Test Method
Density	1.53	g/cm ³	ASTM D1505
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	38	μm	
Secant Modulus - 1% Secant, MD	2790	MPa	ASTM D882
Tensile Strength - MD (Break)	193	MPa	ASTM D882
Tensile Elongation - MD (Break)	90	%	ASTM D882
Elmendorf Tear Strength - MD	18	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
RTI Elec (0.0380 mm)	240	°C	UL 746
RTI Str (0.0380 mm)	210	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Dielectric Strength	180	kV/mm	ASTM D149
Dielectric Constant (1 kHz)	3.20		ASTM D150
Dissipation Factor (1 kHz)	1.2E-3		ASTM D150
Arc Resistance (0.0380 mm)	60.0	sec	ASTM D495
Comparative Tracking Index (CTI) (0.0380 mm)	213	V	UL 746
High Amp Arc Ignition (HAI) (0.0380 mm)	15.0		UL 746

High Voltage Arc Tracking Rate (HVTR) (0.0380 mm)	150	mm/min	UL 746
Hot-wire Ignition (HWI) (0.0380 mm)	120	sec	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.0380 mm)	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

