

Multi-Pro® 1510 CU

Polypropylene

Multibase, A Dow Corning Company

Message:

Multi-Pro® 1510 CU is a Polypropylene product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Primary characteristic: good uv resistance.

General Information			
Features	Good UV Resistance		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.02	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.9	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	25.4	MPa	ASTM D638
Tensile Elongation (Break)	570	%	ASTM D638
Flexural Modulus	1420	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	69	J/m	ASTM D256
Gardner Impact	14.7	J	ASTM D5420
Injection	Nominal Value	Unit	Test Method
Drying Temperature	65.6	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	199	°C	
Middle Temperature	216	°C	
Front Temperature	221	°C	
Nozzle Temperature	227	°C	
Processing (Melt) Temp	227	°C	
Mold Temperature	26.7 to 48.9	°C	
Injection Rate	Moderate-Fast		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT