

# Elvax® 210W

Ethylene Vinyl Acetate Copolymer

DuPont Packaging & Industrial Polymers

## Message:

DuPont™ Elvax® 210W is an ethylene-vinyl acetate copolymer resin for use in industrial applications. This resin is supplied in pellet form and contains a "W" amide additive to improve pellet handling.

### Composition

28 % By Weight Vinyl Acetate comonomer content

Contains a "W" amide additive to improve pellet handling.

Thermal Stabilizer: BHT antioxidant

### Applications

Elvax® resins can be used in a variety of applications involving molding, compounding, extrusion, adhesives, sealants, and wax blends. For additional information and properties associated with specific applications, please refer to the Grade Selector Guides found on the Elvax® website for industrial applications. [http://www2.dupont.com/Elvax/en\\_US/tech\\_info/index.html](http://www2.dupont.com/Elvax/en_US/tech_info/index.html)

General Information			
Additive	Antioxidant		
	Heat Stabilizer		
	Unspecified Additive		
Features	Antioxidant		
	Copolymer		
	Food Contact Acceptable		
	Heat Stabilized		
Uses	Adhesives		
	Blending		
	Compounding		
	Industrial Applications		
	Sealants		
	Wire Jacketing		
Agency Ratings	FDA 21 CFR 177.1350(a)(1)		
Forms	Pellets		
Processing Method	Blow Molding		
	Compounding		
	Compression Molding		
	Extrusion		
	Injection Molding		
	Sheet Extrusion		
	Structural Foam Molding		
Physical	Nominal Value	Unit	Test Method

Specific Gravity	0.951	g/cm <sup>3</sup>	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	400	g/10 min	ASTM D1238, ISO 1133
Vinyl Acetate Content	28.0	wt%	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	39.0	°C	ASTM D1525, ISO 306
Peak Melting Temperature	60.0	°C	ASTM D3418, ISO 3146
Injection	Nominal Value	Unit	
Processing (Melt) Temp	< 230	°C	
Extrusion	Nominal Value	Unit	
Melt Temperature	< 230	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

