

Chemlon® 228 GI

Polyamide 6

Teknor Apex Company (Chem Polymer)

Message:

Chemlon® 228 GI is a Polyamide 6 (Nylon 6) material filled with glass fiber. It is available in Asia Pacific, Europe, or North America for injection molding.

Important attributes of Chemlon® 228 GI are:

Creep Resistant

Good Stiffness

Good Toughness

Impact Modified

General Information			
Filler / Reinforcement	Glass Fiber		
Additive	Impact Modifier		
Features	Good Creep Resistance		
	Good Stiffness		
	Good Toughness		
	Impact Modified		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.29	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	121	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	4.0	%	ASTM D638
Flexural Modulus (23°C)	5170	MPa	ASTM D790
Flexural Strength (23°C)	172	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	160	J/m	ASTM D256
Thermal	Nominal Value	Unit	
Melting Temperature	216	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

