YUNGSOX® PP 1600D

Polypropylene Homopolymer

Formosa Polypropylene

Message:

 $YUNGSOX @ \ PP\ 1600D\ is\ a\ Polypropylene\ Homopolymer\ (PP\ Homopolymer)\ material.\ It\ is\ available\ in\ Asia\ Pacific.$

Important attributes of YUNGSOX $\ensuremath{\mathfrak{B}}$ PP 1600D are:

Fast Molding Cycle

Good Aesthetics

High Flow

Homopolymer

Warp Resistant

Typical applications include:

Containers

Food Contact Applications

Household Applications

General Information					
Features	Fast Molding Cycle				
	High Flow				
	Homopolymer				
	Low Warpage				
	Pleasing Surface Appearance				
Uses	Containers				
	Household Goods				
	Thin-walled Containers				
Agency Ratings	FDA 21 CFR 177.1520				
Forms	Pellets				
Physical	Nominal Value	Unit	Test Method		
Density	0.900	g/cm³	ISO 1183		
Melt Mass-Flow Rate (MFR) (230°C/2.1					
kg)	60	g/10 min	ISO 1133		
Molding Shrinkage	1.3 to 1.7	%	Internal Method		
Hardness	Nominal Value	Unit	Test Method		
Rockwell Hardness (R-Scale)	111		ISO 2039-2		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Stress (Yield)	39.2	MPa	ISO 527-2		
Tensile Strain (Break)	10	%	ISO 527-2		
Flexural Modulus	1620	МРа	ISO 178		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact (23°C)	20	J/m	ISO 180		
Thermal	Nominal Value	Unit	Test Method		

Heat Deflection Temperature (1.8 MPa,					
Unannealed)	120	°C	ISO 75-2/A		
Vicat Softening Temperature	155	°C	ISO 306		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2