

PENTAMID A MK40 H black

Polyamide 66

PENTAC Polymer GmbH

Message:

Normal viscosity, heat stabilised polyamide 66, 40% mineral filled

General Information				
Filler / Reinforcement	Mineral filler, 40% filler by weight			
Additive	heat stabilizer			
Features	Thermal Stability			
Agency Ratings	EC 1907/2006 (REACH)			
Appearance	Black			
Forms	Particle			
Processing Method	Injection molding			
Physical	Dry	Conditioned	Unit	Test Method
Density	1.46	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Transverse flow	0.75	--	%	ISO 294-4
Flow	0.70	--	%	ISO 294-4
Water Absorption				ISO 62
Saturated, 23°C	4.6	--	%	ISO 62
Equilibrium, 23°C, 50% RH	1.4	--	%	ISO 62
Viscosity Number	145	--	cm ³ /g	ISO 307
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	6300	3500	MPa	ISO 527-2/1
Tensile Stress (Break)	85.0	55.0	MPa	ISO 527-2/5
Tensile Strain (Break)	> 10	> 20	%	ISO 527-2/5
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.0	12	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	90 kJ/m ²	No Break		ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	235	--	°C	ISO 75-2/B
1.8 MPa, not annealed	110	--	°C	ISO 75-2/A
Melting Temperature	260	--	°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Dielectric Strength	30	--	kV/mm	IEC 60243-1

Dielectric Constant (1 MHz)	3.40	--		IEC 60250
Comparative Tracking Index	500	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (3.2 mm)	HB	--		UL 94
Additional Information	Dry	Conditioned		Test Method
ISO Shortname	PA66, MHRC, 14-060 N, MD40 --			ISO 1874
Injection	Dry	Unit		
Drying Temperature	80		°C	
Drying Time	3.0		hr	
Suggested Max Moisture	0.040 - 0.12		%	
Suggested Max Regrind	20		%	
Rear Temperature	275 - 295		°C	
Middle Temperature	280 - 305		°C	
Front Temperature	285		°C	
Processing (Melt) Temp	270 - 310		°C	
Mold Temperature	60 - 100		°C	
Injection Pressure	80.0		MPa	
Screw L/D Ratio	18.0:1.0 to 22.0:1.0			
Screw Compression Ratio	2.2:1.0 to 2.8:1.0			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT