

# Gallonprene® GP520-7504

Thermoplastic Elastomer

Shenzhen Sungallon Rubber & Plastic Corporation Limited

## Message:

Gallonprene® GP520-7504 is a thermoplastic elastomer (TPE) product. It can be processed by injection molding and is available in Africa and the Middle East, Latin America or Asia Pacific. Gallonprene® GP520-7504 application areas include engineering/industrial accessories, home applications, consumer goods and handles.

Features include:

Comply with REACH standard

ROHS certification

Halogen-free

General Information			
Features	High elasticity		
	Halogen-free		
Uses	overmolding		
	Household goods		
	Soft handle		
	Toys		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Appearance	White		
	Rough surface polishing		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.09	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/2.16 kg)	10	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 23°C)	75		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Break)	5.60	MPa	ASTM D412
Tensile Elongation <sup>2</sup> (Break)	650	%	ASTM D412
Injection	Nominal Value	Unit	
Rear Temperature	145 - 165	°C	
Middle Temperature	155 - 175	°C	
Front Temperature	165 - 185	°C	
Processing (Melt) Temp	120 - 140	°C	
Mold Temperature	30.0 - 60.0	°C	

Injection Rate	Moderate
Injection instructions	
Processing Temperature Limit: 260°CInjection Pressure: ModerateBack Pressure: 20 to 50%Overmolding Parameters:Rear Temperature: 165 to 185°CCenter Temperature: 175 to 195°CFront Temperature: 185 to 205°C Melt Temperature: 120 to 140°C Mold Temperature: 30 to 60°CProcessing Temperature Limit: 260°CInjection Pressure: ModerateInjection Speed: ModerateBack Pressure: 20 to 50%	
NOTE	
1.	500 mm/min
2.	500 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

