

Niuk 60GP20

Polybutylene Terephthalate

Shanghai Niuk New Plastic Technology Co., Ltd.

Message:

Niuk 60GP20 is a Polybutylene Terephthalate (PBT) material filled with 20% glass fiber. It is available in Asia Pacific.

Important attributes of Niuk 60GP20 are:

Flame Rated

Corrosion Resistant

Heat Resistant

Low Moisture Absorption

Rigid

Typical applications include:

Electrical/Electronic Applications

Engineering/Industrial Parts

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Good Corrosion Resistance		
	Good Electrical Properties		
	High Heat Resistance		
	High Rigidity		
	Low Moisture Absorption		
Uses	Connectors		
	Electrical/Electronic Applications		
	Gears		
	Pump Parts		
	Switches		
	Valves/Valve Parts		
Physical	Nominal Value	Unit	Test Method
Density	1.45	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 2577
Across Flow : 3.20 mm	0.60 to 0.80	%	
Flow : 3.20 mm	1.2 to 1.3	%	
Ash Content	20	%	ISO 3451
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	110	MPa	ISO 527-2/50
Tensile Strain (Break)	3.0	%	ISO 527-2/50
Flexural Modulus ²	5800	MPa	ISO 178
Flexural Stress ³	165	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.0	kJ/m ²	ISO 179

Charpy Unnotched Impact Strength (23°C)	40	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	210	°C	ISO 75-2/B
1.8 MPa, Unannealed	200	°C	ISO 75-2/A
Vicat Softening Temperature	215	°C	ISO 306/B120
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
NOTE			
1.	150x100x3.2 mm		
2.	2.0 mm/min		
3.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

