

OmniTech™ PET GR30

Polyethylene Terephthalate

OMNI Plastics, LLC

Message:

30% Glass Reinforced PET

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.55	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	152	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	8960	MPa	ASTM D790
Flexural Strength	234	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	96	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 3.18 mm)	246	°C	ASTM D648
Flammability	Nominal Value	Test Method	
Flame Rating (3.18 mm)	HB	Internal Method	
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	271 to 293	°C	
Middle Temperature	271 to 293	°C	
Front Temperature	271 to 304	°C	
Nozzle Temperature	271 to 304	°C	
Processing (Melt) Temp	271 to 304	°C	
Mold Temperature	82.2 to 121	°C	
Back Pressure	0.345	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

