

# Kuraray Poval® PVA L-9-78

Polyvinyl Alcohol

Kuraray Co., Ltd.

Message:

Primary suspending agent

| General Information               |  |         |             |
|-----------------------------------|--|---------|-------------|
| Features                          | Biodegradable  |         |             |
|                                   | Water Soluble  |         |             |
| Forms                             | Granules   |         |             |
| Physical                          | Nominal Value  | Unit    | Test Method |
| Solution Viscosity <sup>1</sup>   | 6 to 7   | mPa · s | DIN 53015   |
| Volatile Matter <sup>2</sup>      | < 5.0  | %       |             |
| Degree of Hydrolysis <sup>3</sup> | 77 to 79   | %       |             |
| NOTE                              |  |         |             |
| 1.                                | 4 % aqueous solution at 20 °C<br>determined by Brookfield<br>synchronized-motor rotary-type<br>visometer |         |             |
| 2.                                | After 3 hrs drying at 105°C,<br>Methanol content less than 3%  |         |             |
| 3.                                | Saponification   |         |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT