

SUSTASON PPSU MG

Polyphenylsulfone
Röchling Sustaplast SE & Co. KG

- Message:
- Product characteristics
 - High sterilisation resistance
 - High heat deflection temperature
 - High tensile strength and rigidity
 - Typical fields of application
 - Medical technology

General Information			
Features	High Rigidity		
	High Strength		
Uses	Medical/Healthcare Applications		
Physical	Nominal Value	Unit	Test Method
Density	1.29	g/cm ³	ISO 1183
Water Absorption (Equilibrium, 23°C, 50% RH)	0.60	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2500	MPa	ISO 527-2
Tensile Stress (Yield)	77.0	MPa	ISO 527-2
Tensile Strain (Break)	30	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	10	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	205	°C	ISO 75-2/A
Continuous Use Temperature			
-- ¹	-50.0 to 180	°C	
-- ²	< 210	°C	
CLTE - Flow	5.5E-5	cm/cm/°C	DIN 53752
Thermal Conductivity	0.35	W/m/K	DIN 52612
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Electric Strength	15	kV/mm	IEC 60243-1
Dielectric Constant	3.44		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
3.00 mm	V-0		
6.00 mm	V-0		

NOTE

- | | |
|----|------------|
| 1. | Long Term |
| 2. | Short Term |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT