

SILVER® PC230.LF

Polycarbonate

Guangdong Silver Age Sci & Tech. Co., Ltd

Message:

SILVER® Polycarbonate is applied to many fields, such as automobiles, office automation equipments, electronics, medical equipments and sports equipments. In addition, the custom—made products should be developed by buyers ‘ requirements in order to meet special usage.

Glass Fiber Reinforced PC

Characteristic:

UL-94 V0/3.0mm, PC+PTFE+15%GF, abrasion resistance and good rigidity

Application:

lighting accessory, fire fighting facility

General Information			
Filler / Reinforcement	Glass Fiber		
Features	Flame Retardant		
	Good Abrasion Resistance		
	Good Wear Resistance		
	Semi Rigid		
Uses	Lighting Applications		
	Lighting Fixtures		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.32	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	9.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	80.0	MPa	ASTM D638
Tensile Elongation ² (Break)	3.0	%	ASTM D638
Flexural Modulus ³	3200	MPa	ASTM D790
Flexural Strength ⁴	110	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area) (23°C)	10.0	kJ/m²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	140	°C	ASTM D648
Flammability	Nominal Value	Test Method	
Flame Rating (3.00 mm)	V-0	UL 94	
Injection	Nominal Value	Unit	
Processing (Melt) Temp	265 to 315	°C	
NOTE			
1.	10 mm/min		

2.	10 mm/min
3.	5.5 mm/min
4.	5.5 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

